

BLAST FURNACE – BUSTLE PIPE

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)		Water Addition (%)	Temp. Limit
	Al ₂ O ₃	SiO ₂	Pump	Shotcrete		
LCF 798A	61.5	35.0	2.64 / 165		5.4 - 5.9	1705°C / 3100°F
PUMPLITE 80 LI	42.2	46.7	1.28 / 80	1.49 / 93	21 - 23	1425°C / 2600°F

