

## CASTHOUSE TROUGH / RUNNER – MAINTENANCE

Products	Chemistry (%)				Density (g/cm <sup>3</sup> / lb/ft <sup>3</sup> )	Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiC	SiO <sub>2</sub>	C		
TEK-GUN 408 A	65.9	15.8	10.1	4.0	2.40 / 150	1650°C / 3000°F
DRI-VIBE® 348A	78.0	13.3	2.1	1.0	2.88 / 180	1650°C / 3000°F
DRI-VIBE® 512A	78.3	13.1	1.4	1.1	2.88 / 180	1705°C / 3100°F

