

PUSHER FURNACE – EXTRACTORS

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂		Internal Vibration	External Vibration	
ALAKAST® 90 LC-P	90.2	7.87	2.90 / 181	4.3 - 4.8		1760°C / 3200°F
ALAKAST® 85 LC-P-ES	87.5	8.4	3.01 / 199	6.0 - 7.0		1760°C / 3200°F

