

## Coreless Induction Furnace – Working Lining Iron Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	°C	°F
DRI-VIBE® LGS	0.6	99.0	2.21	138	1650	3000
DRI-VIBE® LGS HTC	0.6	99.0	2.21	138	1650	3000
DRI-VIBE® 461S	0.5	99.2	1.99	124	1650	3000
DRI-VIBE® 462S	0.5	99.2	1.89	118	1650	3000
DRI-VIBE® 799A	79.9	16.8	2.92	182	1700	3100
MINRO-SIL® RAM 1001	0.3	99.0	2.15	134	1650	3000
MINRO-SIL® 2001	0.5	99.2	2.18	136	1650	3000
TEK-SIL	0.1	99.7	2.00	125	1650	3000