

BLAST FURNACE – TUYERE SLEEVE

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition (%)	Temp. Limit
	Al ₂ O ₃	SiO ₂			
LCF 798A	61.5	35.0	2.64 / 165	5.4 - 5.9	1705°C / 3100°F

