

BLAST FURNACE – UPPER STACK

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)		Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	Vibration	Shotcrete	Vibration	Shotcrete	
STACKCRETE® 62M	61.7	32.8	2.45 / 153	2.37 / 148	4.5 - 5.2	5.4 - 6.2	1700°C / 3100°F

