

## PUSHER FURNACE – LEADING EDGE

Products	Chemistry (%)		Density (g/cm <sup>3</sup> / lb/ft <sup>3</sup> )		Water Addition (%)		Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Vibration	Shotcrete	Vibration	Shotcrete	
ALAKAST® 90 LC-P	90.2	7.87	2.90 / 181		4.3 - 4.8		1760°C / 3200°F
TUFF-FLO 98	98.6	1.2	3.03 / 189	-	4.0 - 5.0	4.5 - 5.5	1870°C / 3400°F

