

Ladles – Patching & Maintenance

Copper Alloy

Products	Chemistry (%)		Density		Water Addition (%)	Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	Trowel/ Veneer	°C	°F
PLASTER 55AC	51.6	37.3	2.21	138	10.0-14.0	1640	3000
CW 620 SEAL	58.3	36.3	2.39	149	-	1705	3100
CW 608 SEAL	84.0	10.5	2.32-2.40	145-150	-	1760	3200
CW 85 HS PLASTIC	83.8	9.0	2.92	182	-	1760	3200
RAM MAX BR 70-P	66.0	26.0	2.56-2.63	160-164	-	1760	3200