

## Ladles – Coatings

### Iron Alloy

Products	Chemistry (%)				Density		Water Addition (%)	Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	MgO	C	g/cm <sup>3</sup>	lb/ft <sup>3</sup>		°C	°F
CW 85 KOTE	2.9	9.5	82.2	-	1.54-1.70	96-106	20.0-30.0	-	-
T-COAT® 692M	-	-	56.0	-	2.0	125	18.0-20.0	1650	3000
LADLE WELL	11.0	64.5	-	20.0	1.91	119	-	1540	2800
LADLE WELL SPRAY	11.8	80.6	-	6.5	1.75	109	-	1540	2800