

GUNNING PRODUCTS for ALUMINUM

CHEMICALLY BONDED

Product	Chemical Analysis		Density (g/cm ³ / lb/ft ³)
	Al ₂ O ₃ %	SiO ₂ %	
QUICK-FIRE® 60G	64.4	27.1	2.21 / 138
QUICK-FIRE® 85G	86.7	4.6	2.50 / 156
QUICK-FIRE® ONE 84G	87.2	4.5	2.42 / 151
MATRIFIRE® 60G ACX	63.6	28.1	2.31 / 144
NANO-TEK® 84 AL G	84.5	11.4	2.52 / 157

NON-WETTING

Product	Chemical Analysis		Density (g/cm ³ / lb/ft ³)
	Al ₂ O ₃ %	SiO ₂ %	
MATRIGUN 70 AC-HOT	66.9	28.5	2.24 / 140
MATRIGUN 25 ACX	43.9	40.8	1.96 / 122
MATRILITE 24ACG	43.2	40.0	1.23 / 77
BETAGUN® ABR	73.8	20.0	2.44 / 152
BETAMAX® 24 LT G	42.3	43.0	1.23 / 77

