

## Channel Induction Furnace – Gunning/Repairs

### Copper Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	°C	°F
TEK-GUN 31A	88.6	7.0	3.13	195	1705	3100
GUNMAX® M	55.7	38.1	2.10-2.16	131-135	1650	3000