

PUSHER FURNACE – BUMPER & SKID BLOCKS

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂		Internal Vibration	External Vibration	
ALAKAST® 98 EZC	98.0	0.1	3.11 / 195	3.9 - 4.3		1760°C / 3200°F
ULTRACON 34C	92.8	6.2	189 / 3.03	4.2 - 4.8	3.9 - 4.6	1760°C / 3200°F
ALPHAMAX® T	92.0	7.0	2.90-2.96 / 181-185	4.0%		1870°C / 3400°F

