

PUSHER FURNACE – BURNER WALLS & ROOF

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition	Temperature Limit
	Al ₂ O ₃	SiO ₂			
BLAST KAST® 70 LC	65.3	29.0	2.36 / 148	7.5 - 8.5 %	1650°C (3000°F)
ALAKAST® 65 LC-P	64.7	30.7	2.40 / 150	6.5 - 7.5	1650°C (3000°F)

