

Coreless Induction Furnace – Top Cap Iron Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
DRI-VIBE® 72A	71.4	25.1	2.71	169	1650	3000
DRI-VIBE® 231S-XB	0.2	99.7	1.89	118	1650	3000
DRI-VIBE® LGS 231-XB	0.5	99.2	1.89	11.8	1650	3000
RAM MAX® BR 70P	69.9	23.4	2.56-2.63	160-164	1760	3200