

Coreless Induction Furnace – Working Lining Copper Alloy

Products	Chemistry (%)					Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	SiC	MgO	ZrO ₂	g/cm ³	lb/ft ³	°C	°F
MINRO-SIL® 2001	0.5	99.2	-	-	-	2.18	136	1650	3000
DRI-VIBE® LGS CU	0.6	99.0	-	-	-	2.21	138	1650	3000
DRI-VIBE® 462S	0.5	99.2	-	-	-	1.89	118	1650	3000
DRI-VIBE® 351A	82.5	9.7	4.0	-	-	2.92	182	1500	2730
DRI-VIBE® 31A	88.7	3.6	3.7	-	-	3.04	190	1705	3100
DRI-VIBE® 252A	85.0	0.5	-	10.6	-	3.19	199	1705	3100