

Reverberatory Furnace – Upper Side Wall

Aluminum Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
MATRIPHOS 85 AC	80.7	12.2	2.80	175	1650	3000
MATRIPUMP AR 61	60.8	34.2	2.46 (V) 2.50 (P)	154 (V) 156 (P)	1650	3000
NANO-TEK® 70	68.1	28.6	2.50	156	1705	3100
QUICK-FIRE® 88	88.6	3.5	2.84	177	1650	3000
REDIGUN 85 P	87.3	6.9	2.72	170	1650	3000
TUFF-FLO 60 A	59.6	36.2	2.58	161	1700	3100